



PK475 (v1.0) June 10, 2011

# 100% Material Declaration Data Sheet FFG1760 Virtex-6

**Average Weight: 20.5536 g**

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
<b>Silicon Die (FPGA)</b>				Silicon IC	<b>0.935666</b>	<b>4.552</b>
	Doped silicon	7440-21-3	100.00	Basis	0.935666	
<b>Solder Bump</b>				Die to package	<b>0.048899</b>	<b>0.238</b>
	Tin	7440-31-5	63.00	Basis	0.030806	
	Lead	7439-92-1	37.00	Basis	0.018093	
<b>Die Underfill</b>					<b>0.130000</b>	<b>0.632</b>
	Bisphenol F-type liquid epoxy resin	9003-36-5	20.00	Basis	0.026000	
	Phenolic resin	Trade secret	15.00	Basis	0.019500	
	Bisphenol A-type liquid epoxy resin	25068-38-6	5.00	Basis	0.006500	
	Amine type accelerator	Trade secret	5.00	Basis	0.006500	
	Silicon dioxide	60676-86-0	51.50	Basis	0.066950	
	Carbon black	1333-86-4	1.00	Basis	0.001300	
	Additives	Trade secret	2.50	Basis	0.003250	

100% Material Declaration Data Sheet – FFG1760 Virtex-6



Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
<b>Substrate</b>					<b>5.632439</b>	<b>27.404</b>
<b>Plating</b>	Copper (Cu)	7440-50-8	39.78	Main material	2.240418	
	Nickel (Ni)	7440-02-0	0.42	Main material	0.023850	
	Gold (Au)	7440-57-5	0.09	Main material	0.005167	
<b>Bump</b>	Lead (Pb)	7439-92-1	0.40	Main material	0.022345	
	Tin (Sn)	7440-31-5	0.68	Main material	0.038048	
<b>Copper Foil</b>	Copper (Cu)	7440-50-8	3.52	Main material	0.198108	
<b>Core</b>	Fiberglass	65997-17-3	21.81	Main material	1.228250	
	Epoxy resin	N/A	21.81	Main material	1.228250	
<b>ABF</b>	Bisphenol A-type epoxy resin	25068-38-6	2.57	Main material	0.144500	
	Cyclohexane	108-94-1	2.57	Main material	0.144500	
	N, N-dimethylformamide	68-12-2	2.57	Main material	0.144500	
	Silica powder (Silicon dioxide)	7631-86-9	2.57	Main material	0.144500	
<b>Solder Mask</b>	Levelling agents & others	N/A	0.01	Main material	0.000560	
	Phthalocyanine blue, organic pigment	N/A	0.00	Main material	0.000140	
	Amine compound	N/A	0.00	Main material	0.000280	
	Barium sulfate	7727-43-7	0.17	Main material	0.009520	
	Silica	15468-32-3	0.08	Main material	0.004760	
	Talc	14807-96-6	0.08	Main material	0.004760	
	Diethylene glycol monoethyl ether acetate	N/A	0.04	Main material	0.002520	
	Dipropylane glycol monomethyl ether	N/A	0.04	Main material	0.002170	
	Dipropylane glycol monomethyl ether acetate	N/A	0.11	Main material	0.006370	
	High boiling-point petroleum solvent	N/A	0.09	Main material	0.005320	
	Aromatic carbonyl compound	N/A	0.03	Main material	0.001890	
	Acrylic monomer	N/A	0.04	Main material	0.002380	
	Acrylic resin	N/A	0.33	Main material	0.018691	
	Epoxy resin	N/A	0.19	Main material	0.010640	

100% Material Declaration Data Sheet – FFG1760 Virtex-6



Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
<b>Solder Paste</b>					<b>0.083000</b>	<b>0.404</b>
	Tin	7440-31-5	96.50	Basis	0.080095	
	Silver	7440-22-4	3.00	Basis	0.002490	
	Copper	7440-50-8	0.50	Basis	0.000415	
<b>Capacitor 0805_X7S</b>					<b>0.056000</b>	<b>0.272</b>
	Ceramic (BaTiO3 type)	Trade secret	61.80	Ceramic	0.034608	
	Inner electrode (Ni)	7440-02-0	27.00	Inner electrode	0.015120	
	Outer electrode (Cu)	7440-50-8	9.90	Outer electrode	0.005544	
	Plating1 (Ni)	7440-02-0	0.40	Plating1	0.000224	
	Plating2 (Sn)	7440-31-5	0.90	Plating2	0.000504	
<b>Capacitor 0603_X7S</b>					<b>0.081900</b>	<b>0.398</b>
	Ceramic (BaTiO3 type)	Trade secret	67.40	Ceramic	0.055201	
	Inner electrode (Ni)	7440-02-0	17.00	Inner electrode	0.013923	
	Outer electrode (Cu)	7440-50-8	13.80	Outer electrode	0.011302	
	Plating1 (Ni)	7440-02-0	0.50	Plating1	0.000410	
	Plating2 (Sn)	7440-31-5	1.30	Plating2	0.001065	
<b>Capacitor 0201_X6S</b>					<b>0.005400</b>	<b>0.026</b>
	Ceramic (BaTiO3 type)	Trade secret	66.00	Ceramic	0.003564	
	Inner electrode (Ni)	7440-02-0	2.67	Inner electrode	0.000144	
	Outer electrode (Cu)	7440-50-8	23.33	Outer electrode	0.001260	
	Plating1 (Ni)	7440-02-0	2.33	Plating1	0.000126	
	Plating2 (Sn)	7440-31-5	5.67	Plating2	0.000306	
<b>Heat Sink</b>					<b>11.900000</b>	<b>57.898</b>
	Copper	7440-50-8	97.94	Main material	11.654860	
	Nickel	7440-02-0	2.06	Main material	0.245140	
<b>Heat Sink Adhesive</b>					<b>0.210000</b>	<b>1.022</b>
	Aluminium Oxide	1344-28-1	70.00	Main material	0.147000	
	Zinc Oxide	1314-13-2	15.00	Main material	0.031500	
	Silicone	Trade Secret	15.00	Main material	0.031500	
	Additive	Trade Secret		Additive		
<b>Solder Balls</b>					<b>1.470244</b>	<b>7.153</b>
	Tin (Sn)	7440-31-5	96.50	Base metal	1.418785	
	Silver (Ag)	7440-22-4	3.00	Base metal	0.044107	
	Copper (Cu)	7440-50-8	0.50	Base metal	0.007351	

## Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
6/10/11	1.0	Initial Xilinx release.

## Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.