

PCN98007 Data

Package Qualification Testing Data for Mold Compound MP8000

Lot #	Part	Package	Test	Quantity	Hours/Cy	Fails	Status
X4983	XC4010™	PC84	85/85	76	48	0	continue
X4983	XC4010	PC84	85/85	76	168	0	continue
X4983	XC4010	PC84	85/85	76	256	0	continue
X4983	XC4010	PC84	85/85	76	500	0	continue
X4983	XC4010	PC84	85/85	76	1016	0	complete
X4984	XC4010	PC84	T/C	74	50	0	continue
X4984	XC4010	PC84	T/C	74	100	0	continue
X4984	XC4010	PC84	T/C	74	250	0	continue
X4984	XC4010	PC84	T/C	74	500	0	continue
X4984	XC4010	PC84	T/C	74	1000	0	complete
X4985	XC4010	PC84	PCT	76	48	0	continue
X4985	XC4010	PC84	PCT	76	96	0	continue
X4985	XC4010	PC84	PCT	76	168	0	complete

Preconditioning: Jedec Level 3 all tests	0/226
Mark Permanency	0/3
Physical Dimensions	0/3
Bond Pull	0/3

Lot #	Part	Package	Test	Quantity	Hours/Cy	Fails	Status
X4983	XC4025E™	PQ240	85/85	76	48	0	continue
X4983	XC4025E	PQ240	85/85	76	168	0	continue
X4983	XC4025E	PQ240	85/85	76	256	0	continue
X4983	XC4025E	PQ240	85/85	76	500	0	continue
X4983	XC4025E	PQ240	85/85	76	1000	0	complete
X4984	XC4025E	PQ240	T/C	76	50	0	continue
X4984	XC4025E	PQ240	T/C	76	100	0	continue
X4984	XC4025E	PQ240	T/C	76	250	0	continue
X4984	XC4025E	PQ240	T/C	76	500	0	continue
X4984	XC4025E	PQ240	T/C	76	1000	0	complete
X4985	XC4025E	PQ240	PCT	76	48	0	continue
X4985	XC4025E	PQ240	PCT	76	96	0	continue
X4985	XC4025E	PQ240	PCT	76	168	0	complete
X4986	XC4025E	PQ240	HAST	12	50	0	continue
X4986	XC4025E	PQ240	HAST	12	100	0	complete

Preconditioning: Jedec Level 3 all tests	0/240
Mark Permanency	0/3
Physical Dimensions	0/5