



100% Material Declaration Data Sheet for FFG1148

PK093 (v1.4) May 13, 2016

Average Weight : 10.8691 g

Component	Substance Description	CAS # or Description	% of Component	Use in product	Component Weight	Component % of total
Silicon Die					0.694500	6.390%
	Silicon	7440-21-3	100.000		0.694500	
Solder Bump					0.036115	0.332%
	Tin	7440-31-5	63.000		0.022753	
	Lead	7439-92-1	37.000		0.013363	
Underfill					0.074000	0.681%
	Silica	60676-86-0	70.000		0.051800	
	Epoxy Resin A	9003-36-5	20.000		0.014800	
	Epoxy Resin B	25068-38-6	3.000		0.002220	
Heat Spreader					6.000000	55.203%
	Copper	7440-50-8	99.900		5.994000	
	Nickel	7440-02-0	0.100		0.006000	
Heat Spreader Adhesive					0.130000	1.196%
	Organopolysiloxane mixture	NA	100.000		0.130000	
Solder Ball					0.959000	8.823%
	Tin	7440-31-5	95.500		0.915845	
	Silver	7440-22-4	4.000		0.038360	
	Copper	7440-50-8	0.500		0.004795	
Substrate					2.975310	27.375%
	Copper	7440-50-8	50.17	metal layer	1.492713	
	Tin	7440-31-5	0.76	metal layer	0.022612	
	Lead	7439-92-1	0.15	metal layer	0.004463	
	Silver	7440-22-4	0.02		0.000595	
	Core	N/A	34.56		1.028267	
	ABF	N/A	12.05		0.358525	
Solder Mask	N/A	2.30		0.068432		

Revision History

Date	Version	Description of Revisions
03/14/2006	1.0	Initial Initial release.
06/01/2006	1.1	100% Material Declaration.
09/27/2006	1.2	Updated component descriptions.
07/20/2010	1.3	Updated Heat Spreader substance description
05/13/2016	1.4	Updated substrate

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.