

**100% Material Declaration Data Sheet:
FG400****Average Weight: 1.94g**

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (Grams)	Component Percent of Total
Silicon Die					0.04944	2.55%
	Silicon	7440-21-3	100.00		0.04944	
Die Attach Material					0.00792	0.41%
	Polymetric Resin	Trade Secret	3.00		0.00023766	
	Diester Resin	Trade Secret	20.00		0.00158440	
	Acrylate Resin	Trade Secret	7.00		0.00055454	
	Silver	7440-22-4	70.00		0.00554540	
Mold Compound					0.00175	0.09%
	SiO2 Filler	60676-86-0	86.20	Filler	0.00150850	
	Epoxy Resin A	Trade Secret	3.00		0.00005250	
	Epoxy Resin B	Trade Secret	3.00		0.00005250	
	Phenol Resin A	Trade Secret	3.00		0.00005250	
	Phenol Resin B	Trade Secret	3.00		0.00005250	
	Metal Hydroxide	Trade Secret	1.50		0.00002625	
	Carbon Black	1333-86-4	0.30		0.00000525	
Substrate					1.53596	79.17%
	Copper	7440-50-8	46.27	Metal Layer	0.71068869	
	Nickel	7440-02-0	0.60	Metal Layer	0.00921576	
	Gold	7440-57-5	0.13	Metal Layer	0.00199675	
	Glass Fiber (GF)	N/A	23.00		0.35327080	
	Halogen Fire Retardant	N/A	3.20		0.04915072	
	BT (core)	N/A	16.80		0.25804128	
	Solder Mask (EP)	N/A	10.00		0.15359600	
Gold Wire					0.01078	0.56%
	Gold	7440-57-5	100.00		0.01078	
Solder Balls					0.33415	17.22%
	Tin	7440-31-5	63.00		0.2105145	
	Lead	7439-92-1	37.00		0.1236355	

Revision History

The following table shows the revision history for this document.

Date	Version	Revision
09/14/06	1.0	Initial Xilinx release.
01/08/07	1.0.1	Corrected CAS number entries for gold wire and solder balls, lead.
12/12/08	1.0.2	Tech Pubs' edit.

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.