



100% Material Declaration Data Sheet FF1156

PK398 (v1.2) March 29, 2013

Average Weight: 11.2247g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die				Silicon IC	0.77363	6.892
	Doped silicon	7440-21-3	100.00	Basis	0.77363	
Solder Bump				Die to package	0.258210	2.300
	Tin (Sn)	7440-31-5	63.00	Basis	0.162672	
	Lead (Pb)	7439-92-1	37.00	Basis	0.095538	
Die Underfill					0.130000	1.158
	Bisphenol F-type liquid epoxy resin	9003-36-5	15.00	Basis	0.019500	
	Phenolic resin	Trade secret	15.00	Basis	0.019500	
	Bisphenol A-type liquid epoxy resin	25068-38-6	5.00	Basis	0.006500	
	Amine type accelerator	Trade secret	5.00	Basis	0.006500	
	Silicon dioxide	60676-86-0	54.00	Basis	0.070200	
	Carbon black	1333-86-4	1.00	Basis	0.001300	
	Additives	Trade secret	5.000	Basis	0.006500	
Heat Spreader					4.989300	44.449
	Copper (Cu)	7440-50-8	98.65	Main material	4.921944	
	Nickel (Ni)	7440-02-0	1.35	Main material	0.067356	
Heat Spreader Adhesive					0.152000	1.354
	Organopolysiloxane mixture	N/A	100.00	Main material	0.152000	
Substrate					3.743	33.346
	Copper	7440-50-8	37.54	Main material	1.405000	
	Nickel	7440-02-0	0.61	Main material	0.023000	
	Gold	7440-57-5	0.19	Main material	0.007000	
	Lead	7439-92-1	0.48	Main material	0.018000	
	Tin	7440-31-5	0.83	Main material	0.031000	
	Core	NA	44.54	Main material	1.667000	
	ABF	NA	15.70	Main material	0.588000	
	Solder mask	N/A	0.11	Main material	0.004000	

© Copyright 2011-2013 Xilinx, Inc. XILINX, the Xilinx logo, Virtex, Spartan, ISE, and other designated brands included herein are trademarks of Xilinx in the United States and other countries. All other trademarks are the property of their respective owners

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Capacitor 1					0.041280	0.368
	Ceramic (BaTiO ₃)	N/A	61.80	Ceramic	0.025511	
	Inner electrode (Ni)	7440-02-0	27.00	Inner electrode	0.011146	
	Outer electrode (Cu)	7440-50-8	9.90	Outer electrode	0.004087	
	Plating 1 (Ni)	7440-02-0	0.40	Plating1	0.000165	
	Plating 2 (Sn)	7440-31-5	0.90	Plating2	0.000372	
Capacitor 2					0.039600	0.353
	Ceramic (BaTiO ₃)	N/A	67.40	Ceramic	0.026690	
	Inner electrode (Ni)	7440-02-0	17.00	Inner electrode	0.006732	
	Outer electrode (Cu)	7440-50-8	13.80	Outer electrode	0.005465	
	Plating 1 (Ni)	7440-02-0	0.50	Plating1	0.000198	
	Plating 2 (Sn)	7440-31-5	1.30	Plating2	0.000515	
Solder Ball					1.097660	9.779
	Tin (Sn)	7440-31-5	63.00	Main material	0.691526	
	Lead (Pb)	7439-92-1	37.00	Main material	0.406134	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
11/02/09	1.0	Initial Xilinx release.
08/03/10	1.1	Updated average weight. Updated component percentage of total for all components. Added substances and corresponding data to ink and substrate components.
07/22/11	1.1.1	Change CAS# for N, N-dimethylformamide from 68-12-1 to 68-12-2
03/29/13	1.2	Updated Substrate Component.

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.