



100% Material Declaration Data Sheet FFG1759

PK434 (v1.1) March 29, 2013

Average Weight: 15.4006 g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die				Silicon IC	0.656000	4.260
	Doped silicon	7440-21-3	100.00	Basis	0.656000	
Solder Bump				Die to package	0.050631	0.329
	Tin	7440-31-5	63.00	Basis	0.031898	
	Lead	7439-92-1	37.00	Basis	0.018734	
Die Underfill					0.130000	0.844
	Bisphenol F-type liquid epoxy resin	9003-36-5	20.00	Basis	0.026000	
	Phenolic resin	Trade secret	15.00	Basis	0.019500	
	Bisphenol A-type liquid epoxy resin	25068-38-6	5.00	Basis	0.006500	
	Amine type accelerator	Trade secret	5.00	Basis	0.006500	
	Silicon dioxide	60676-86-0	51.50	Basis	0.066950	
	Carbon black	1333-86-4	1.00	Basis	0.001300	
	Additives	Trade secret	2.50	Basis	0.003250	
Solder Paste					0.105000	0.682
	Tin	7440-31-5	96.50	Basis	0.101325	
	Silver	7440-22-4	3.00	Basis	0.003150	
	Copper	7440-50-8	0.50	Basis	0.000525	
Substrate					5.285891	34.323
	Copper	7440-50-8	33.432	Main material	1.767183	
	Nickel	7440-02-0	0.418	Main material	0.022095	
	Gold	7440-57-5	0.091	Main material	0.004787	
	Lead	7439-92-1	0.611	Main material	0.032301	
	Tin	7440-31-5	1.040	Main material	0.054998	
	Core	N/A	46.473	Main material	2.456500	
	ABF	N/A	16.402	Main material	0.867000	
	Solder mask	N/A	1.533	Main material	0.081027	

© Copyright 2011-2013 Xilinx, Inc. XILINX, the Xilinx logo, Virtex, Spartan, ISE, and other designated brands included herein are trademarks of Xilinx in the United States and other countries. All other trademarks are the property of their respective owners

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Capacitor 1					0.056000	0.364
	Ceramic (BaTiO3 type)	Trade secret	61.80	Ceramic	0.034608	
	Inner electrode (Ni)	7440-02-0	27.00	Inner electrode	0.015120	
	Outer electrode (Cu)	7440-50-8	9.90	Outer electrode	0.005544	
	Plating1 (Ni)	7440-02-0	0.40	Plating1	0.000224	
	Plating2 (Sn)	7440-31-5	0.90	Plating2	0.000504	
Capacitor 2					0.074100	0.481
	Ceramic (BaTiO3 type)	Trade secret	67.40	Ceramic	0.049943	
	Inner electrode (Ni)	7440-02-0	17.00	Inner electrode	0.012597	
	Outer electrode (Cu)	7440-50-8	13.80	Outer electrode	0.010226	
	Plating1 (Ni)	7440-02-0	0.50	Plating1	0.000371	
	Plating2 (Sn)	7440-31-5	1.30	Plating2	0.000963	
Heat Sink					7.310000	47.466
	Copper	7440-50-8	98.65	Main material	7.211315	
	Nickel	7440-02-0	1.35	Main material	0.098685	
Heat Sink Adhesive					0.260000	1.688
	Aluminum dioxide	1344-28-1	70.00	Main material	0.182000	
	Zinc oxide	1314-13-2	15.00	Main material	0.039000	
	Organic silicon compound	trade secret	15.00	Main material	0.039000	
Solder Balls					1.473000	9.565
	Tin (Sn)	7440-31-5	95.50	Main material	1.406715	
	Silver (Ag)	7440-22-4	4.00	Main material	0.058920	
	Copper (Cu)	7440-50-8	0.50	Main material	0.007365	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
03/11/11	1.0	Initial Xilinx release.
03/29/13	1.1	Updated Substrate Component

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.