



100% Material Declaration Data Sheet for 7 Series FFG676

PK548 (v1.1) January 25, 2013

Average Weight: 7.8820 g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die					0.388303	4.926
	Silicon (Si)	7440-21-3	100.00	Basis	0.388303	
Solder Bump					0.018136	0.230
	Tin (Sn)	7440-31-5	63.00	Basis	0.011426	
	Lead (Pb)	7439-92-1	37.00	Basis	0.006710	
Solder Paste					0.005400	0.069
	Tin (Sn)	7440-31-5	96.50	Metal	0.005211	
	Silver (Ag)	7440-22-4	3.00	Metal	0.000162	
	Copper (Cu)	7440-50-8	0.50	Metal	0.000027	
Capacitor 1					0.021600	0.274
	Ceramic (BaTiO3 type)	12047-27-7	70.60	Ceramic	0.015250	
	Nickel (Ni)	7440-02-0	6.70	Inner electrode	0.001447	
	Copper (Cu)	7440-50-8	20.10	Outer electrode	0.004342	
	Nickel (Ni)	7440-02-0	0.80	Plating1	0.000173	
	Tin (Sn)	7440-31-5	1.80	Plating2	0.000389	
Capacitor 2					0.003800	0.048
	Ceramic (BaTiO3 type)	12047-27-7	61.70	Ceramic	0.002345	
	Nickel (Ni)	7440-02-0	4.89	Inner electrode	0.000186	
	Indium Tin Oxide	50926-11-9	18.30	Outer electrode	0.000695	
	Copper (Cu)	7440-50-8	13.40	Outer electrode	0.000509	
	Nickel (Ni)	7440-02-0	0.49	Plating1	0.000019	
	Tin (Sn)	7440-31-5	1.22	Plating2	0.000046	
Capacitor 3					0.001200	0.015
	Ceramic (BaTiO3 type)	12047-27-7	66.00	Ceramic	0.000792	
	Inner electrode (Ni)	7440-02-0	2.67	Inner electrode	0.000032	
	Outer electrode (Cu)	7440-50-8	23.33	Outer electrode	0.000280	
	Plating 1 (Ni)	7440-02-0	2.33	Plating1	0.000028	
	Plating 2 (Sn)	7440-31-5	5.67	Plating2	0.000068	

© Copyright 2013 Xilinx, Inc. XILINX, the Xilinx logo, Virtex, Spartan, ISE, and other designated brands included herein are trademarks of Xilinx in the United States and other countries. All other trademarks are the property of their respective owners

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Capacitor 4					0.007360	0.093
	BaTiO3 type	12047-27-7	51.10	Ceramic	0.003761	
	Inner Electrode(Ni)	7440-02-0	27.00	Inner electrode	0.001987	
	Outer Electrode(Cu)	7440-50-8	16.00	Outer Electrode	0.001178	
	Glass	65997-17-3	0.90		0.000066	
	Plating1(Ni)	7440-02-0	2.00	Plating1	0.000147	
	Plating2(Sn)	7440-31-5	3.00	Plating2	0.000221	
Underfill					0.049000	0.622
	Bisphenol F/ epichlorohydrin copolymer	9003-36-5	20.00	basis	0.009800	
	Phenolic resin	trade secret	15.00	basis	0.007350	
	Bisphenol A type liquid epoxy resin	25068-38-6	5.00	basis	0.002450	
	Amine type accelerator	trade secret	5.00	basis	0.002450	
	Silicon dioxide	60676-86-0	51.50	basis	0.025235	
	Carbon black	1333-86-4	1.00	basis	0.000490	
	Additives	trade secret	2.50	Additive	0.001225	
Lid					4.615000	58.551
	Copper (Cu)	7440-50-8	97.94	Main material	4.519931	
	Nickel (Ni)	8049-31-8	2.06	Main material	0.095069	
Lid Adhesive					0.115000	1.459
	Aluminium Oxide	1344-28-1	70.00	Main material	0.080500	
	Dimethyl siloxane, dimethylvinyl-terminated	68083-19-2	30.00	Main material	0.034500	
Solder Ball					0.564707	7.165
	Tin (Sn)	7440-31-5	96.50	Main material	0.544942	
	Silver (Ag)	7440-22-4	3.00	Main material	0.016941	
	Copper (Cu)	7440-50-8	0.50	Main material	0.002824	
Substrate					2.092494	26.548
	Copper (Cu)	7440-50-8	40.50		0.847460	
	Tin (Sn)	7440-31-5	1.13		0.023645	
	Lead (Pb)	7439-92-1	0.29		0.006068	
	Silver (Ag)	7440-22-4	0.02		0.000418	
	BT Core	N/A	42.70		0.893495	
	ABF	N/A	13.17		0.275581	
	Solder Mask	N/A	2.19		0.045826	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
03/23/12	1.0	Initial Xilinx release.
01/25/13	1.1	Update substrate component

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.