

Average Weight: 14.3655g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die					0.446519	3.108%
	Silicon (Si)	7440-21-3	100.00	Basis	0.446519	
Solder Bump					0.029370	0.204%
	Tin (Sn)	7440-31-5	63.00	Basis	0.018503	
	Lead (Pb)	7439-92-1	37.00	Basis	0.010867	
Solder Paste					0.005900	0.041%
	Tin (Sn)	7440-31-5	96.50	metal	0.005694	
	Silver (Ag)	7440-22-4	3.00	metal	0.000177	
	Copper (Cu)	7440-50-8	0.50	metal	0.000030	
Capacitor 1					0.037800	0.263%
	Barium oxide	1304-28-5	37.46	Ceramic	0.014160	
	Titanium dioxide	13463-67-7	18.73	Ceramic	0.007080	
	Misc.	trade secret	6.24	Ceramic	0.002359	
	Nickel (Ni)	7440-02-0	17.95	Inner electrode	0.006785	
	Copper (Cu)	7440-50-8	15.88	Outer electrode	0.006003	
	Silicon dioxide	7631-86-9	1.41	Outer electrode	0.000533	
	Boric oxide	1303-86-2	0.35	Outer electrode	0.000132	
	Nickel (Ni)	7440-02-0	0.54	Nickel Plating Layer	0.000204	
	Tin (Sn)	7440-31-5	1.44	Tin Plating Layer	0.000544	
Capacitor 2					0.004800	0.033%
	Barium oxide	1304-28-5	40.00	Ceramic	0.001920	
	Titanium dioxide	13463-67-7	20.00	Ceramic	0.000960	
	Misc.	trade secret	6.67	Ceramic	0.000320	
	Nickel (Ni)	7440-02-0	2.42	Inner electrode	0.000116	
	Copper (Cu)	7440-50-8	20.73	Outer electrode	0.000995	
	Silicon dioxide	7631-86-9	1.85	Outer electrode	0.000089	
	Boric oxide	1303-86-2	0.45	Outer electrode	0.000022	
	Nickel (Ni)	7440-02-0	2.12	Nickel Plating Layer	0.000102	
	Tin (Sn)	7440-31-5	5.76	Tin Plating Layer	0.000276	

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Capacitor 3					0.007360	0.051%
	Barium oxide	1304-28-5	31.67	Ceramic	0.002331	
	Titanium dioxide	13463-67-7	15.83	Ceramic	0.001165	
	Misc.	trade secret	5.28	Ceramic	0.000389	
	Nickel (Ni)	7440-02-0	26.67	Inner electrode	0.001963	
	Copper (Cu)	7440-50-8	15.10	Outer electrode	0.001111	
	Silicon dioxide	7631-86-9	1.34	Outer electrode	0.000099	
	Boric oxide	1303-86-2	0.33	Outer electrode	0.000024	
	Nickel (Ni)	7440-02-0	1.00	Nickel Plating Layer	0.000074	
	Tin (Sn)	7440-31-5	2.78	Tin Plating Layer	0.000205	
Underfill					0.051000	0.355%
	Bisphenol F/ epichlorohydrin copolymer	9003-36-5	20.00	basis	0.010200	
	Phenolic resin	trade secret	15.00	basis	0.007650	
	Bisphenol A type liquid epoxy resin	25068-38-6	5.00	basis	0.002550	
	Amine type accelerator	trade secret	5.00	basis	0.002550	
	Silicon dioxide	60676-86-0	51.50	filler	0.026265	
	Carbon black	1333-86-4	1.00	color agent	0.000510	
	Additives	trade secret	2.50	additives	0.001275	
Lid					9.030000	62.859%
	Copper (Cu)	7440-50-8	98.35	Main Material	8.881005	
	Nickel (Ni)	7440-02-0	1.65	Main Material	0.148995	
Lid Adhesive					0.168000	1.169%
	Aluminium Oxide Al ₂ O ₃	1344-28-1	70.00	Main Material	0.117600	
	Dimethyl siloxane, dimethylvinyl-terminated	68083-19-2	30.00	Main Material	0.050400	
Solder Ball					1.100278	7.659%
	Tin (Sn)	7440-31-5	63.00	Main material	0.693175	
	Lead (Pb)	7439-92-1	37.00	Main material	0.407103	

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Substrate					3.484468	24.256%
	Copper (Cu)	7440-50-8	41.15		1.433859	
	Tin (Sn)	7440-31-5	0.86		0.029966	
	Lead (Pb)	7439-92-1	0.20		0.006969	
	Silver (Ag)	7440-22-4	0.02		0.000697	
	BT Core	N/A	44.01		1.533514	
	ABF	N/A	11.50		0.400714	
	Solder Mask	N/A	2.26		0.078749	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
04/10/2015	1.0	Initial Xilinx release

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.