



100% Material Declaration Data Sheet for FFV1136

PK788 (v1.0) Apr 1, 2016

Average Weight : 10.1412 g

Component	Substance Description	CAS # or Description	% of component	Use in product	Component weight / substance weight (in grams)	Component % of total
Silicon die	Si	7440-21-3	100.00	basis	0.248141	2.447%
					0.248141	
Bump	Sn	7440-31-5	98.20	basis	0.007615	0.076%
	Ag	7440-22-4	1.80	basis	0.000140	
Underfill					0.040000	0.394%
	Bisphenol F type liquid epoxy resin	9003-36-5	15.00	basis	0.006000	
	1,6-Bis(2,3-epoxypropoxy)naphthalene	27610-48-6	10.00	basis	0.004000	
	Bisphenol A type liquid epoxy resin	25068-38-6	5.00	basis	0.002000	
	Amine type hardener	trade secret	10.00	basis	0.004000	
	Silicon dioxide	60676-86-0	58.00	filler	0.023200	
	Carbon black	1333-86-4	1.00	color agent	0.000400	
Additives	trade secret	1.00	additives	0.000400		
Solder paste					0.006464	0.064%
	Sn	7440-31-5	96.50	metal	0.006238	
	Ag	7440-22-4	3.00	metal	0.000194	
Capacitor 1					0.000032	0.568%
					0.057600	
	BaTiO3 type	1304-28-5	37.46	Ceramic	0.021577	
	Titanium dioxide	13463-67-7	18.73		0.010788	
	Misc	-	6.24		0.003594	
	Ni	7440-02-0	17.95	Inner electrode	0.010339	
	Cu	7440-50-8	15.88	Out electrode	0.009147	
	Silicon dioxide	7631-86-9	1.41		0.000812	
	diboron trioxide; boric oxide	1303-86-2	0.35		0.000202	
	Ni	7440-02-0	0.54	Plating1	0.000311	
Sn	7440-31-5	1.44	Plating2	0.000829		
Capacitor2					0.013760	0.136%
	BaTiO3 type	1304-28-5	34.54	Ceramic	0.004753	
	Titanium dioxide	13463-67-7	17.27		0.002376	
	Misc	-	5.76		0.000793	
	Ni	7440-02-0	31.90	Inner Electrode	0.004389	
	Cu	7440-50-8	8.52	Outer Electrode	0.001172	
	Silicon dioxide	7631-86-9	0.76		0.000105	
	diboron trioxide; boric oxide	1303-86-2	0.19		0.000026	
	Ni	7440-02-0	0.29	Plating1	0.000040	
	Sn	7440-31-5	0.77	Plating2	0.000106	
Lid					5.095800	50.249%
	Cu	7440-50-8	98.35	Main material	5.011719	
Lid adhesive					0.084081	1.148%
	Ni	7440-02-0	1.65	Main material	0.084081	
	Aluminium Oxide Al2O3	-	80.00	Main material	0.093120	
Solder ball					0.023280	9.383%
	Dimethyl siloxane, dimethylvinyl-terminated	68083-19-2	20.00	Main material	0.023280	
Solder ball					0.951543	9.383%
	Sn	7440-31-5	96.50	Main material	0.918239	
	Ag	7440-22-4	3.00	Main material	0.028546	
Substrate					0.004758	35.534%
					3.603537	
	Copper	7440-50-8	30.84		1.111331	
	Tin	7440-31-5	1.13		0.040720	
	Silver	7440-22-4	0.10		0.003604	
	Copper	7440-50-8	0.04		0.001441	
	Core	N/A	45.88		1.653303	
	PP	N/A	6.02		0.216933	
	ABF	N/A	14.00		0.504495	
Solder Mask	N/A	2.00		0.072071		

Revision History

Date	Version	Description of Revisions
04/01/2016	1	Initial Xilinx release.

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.