

100% Material Declaration Data Sheet for RF1930

Average Weight : 33.9868 g

Component	Substance Description	CAS # or Description	% of component	Use in product	Component weight / substance weight (in grams)	Component % of total
Silicon die	Silicon	7440-21-3	100.00	Basis	0.893576	2.629%
					0.893576	
Bump	Tin	7440-31-5	63.00	Basis	0.043334	0.128%
	Lead	7439-92-1	37.00	Basis	0.016034	
					0.093450	0.275%
Underfill	Bisphenol F/ epichlorohydrin copolymer	9003-36-5	20.00	Basis	0.018690	
	Phenolic resin	trade secret	15.00	Basis	0.014018	
	Bisphenol A type liquid epoxy resin	25068-38-6	5.00	Basis	0.004673	
	Amine type accelerator	trade secret	5.00	Basis	0.004673	
	Silicon dioxide	60676-86-0	51.50	Basis	0.048127	
	Carbon black	1333-86-4	1.00	Basis	0.000935	
	Additives	trade secret	2.50	Additive	0.002336	
					0.009288	0.027%
Solder Paste	Tin	7440-31-5	63.00	Metal	0.005851	
	Lead	7439-92-1	37.00	Metal	0.002165	
					0.041280	0.121%
Capacitor 1	Barium	12047-27-7	88.86	Ceramic	0.036680	
	Manganese	1313-13-9	1.43	Ceramic	0.000590	
	Nickel	7440-02-0	4.29	Internal Electrode	0.001769	
	Copper	7440-50-8	0.70	Termination	0.000289	
	Boron	1303-86-2	0.01	Termination	0.000006	
	Nickel	7440-02-0	3.57	Plating	0.001474	
	Tin	7440-31-5	0.90	Plating	0.000372	
	Lead	7439-92-1	0.24	Plating	0.000100	
					0.016400	0.048%
Capacitor 2	Barium	12047-27-7	88.86	Ceramic	0.014573	
	Manganese	1313-13-9	1.43	Ceramic	0.000234	
	Nickel	7440-02-0	4.29	Internal Electrode	0.000703	
	Copper	7440-50-8	0.70	Termination	0.000115	
	Glass oxide	65997-17-3	0.01	Termination	0.000002	
	Nickel	7440-02-0	3.57	Plating	0.000586	
	Tin	7440-31-5	0.86	Plating	0.000141	
	Lead	7439-92-1	0.29	Plating	0.000047	
					0.003125	0.009%
Capacitor 3	Barium	12047-27-7	71.29	Ceramic	0.002228	
	Manganese	1313-13-9	10.43	Ceramic	0.000326	
	Nickel	7440-02-0	2.00	Internal Electrode	0.000063	
	Copper	7440-50-8	11.57	Termination	0.000362	
	Boron	1303-86-2	0.21	Termination	0.000007	
	Nickel	7440-02-0	1.80	Plating	0.000056	
	Gold	7440-57-5	2.70	Plating	0.000084	
					0.015456	0.045%
Capacitor 4	Barium	12047-27-7	0.72	Ceramic	0.000112	
	Manganese	1313-13-9	0.11	Ceramic	0.000016	
	Nickel	7440-02-0	0.04	Internal Electrode	0.000006	
	Copper	7440-50-8	0.06	Termination	0.000009	
	Glass oxide	65997-17-3	0.00	Termination	0.000000	
	Nickel	7440-02-0	0.03	Plating	0.000004	
	Tin	7440-31-5	0.04	Plating	0.000006	
	Lead	7439-92-1	0.00	Plating	0.000001	
					22.670000	66.702%
Heat sink	Copper	7440-50-8	98.35	Main material	22.295945	
	Nickel	7440-02-0	1.65	Main material	0.374055	
					0.228000	0.671%
Heat sink adhesive	Aluminium Oxide Al2O3	1344-28-1	70.00	Main material	0.159600	
	Dimethyl siloxane, dimethylvinyl-terminated	68083-19-2	30.00	Main material	0.068400	
					1.836968	5.405%
Solder ball	Tin	7440-31-5	63.00	Main material	1.157290	
	Lead	7439-92-1	37.00	Main material	0.679678	
					8.109123	23.860%
Substrate	Copper	7440-50-8	39.00		3.212024	
	Tin	7440-31-5	0.30		0.026760	
	Lead	7439-92-1	0.20		0.015407	
	Core	N/A	40.00		3.271220	
	ABF	N/A	18.00		1.471806	
	Solder mask	N/A	1.40		0.111095	

0

Revision History

Date	Version	Description of Revisions
6/23/2016	1.0	Initial Xilinx release.

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.