



PK858(v1.0) January 19, 2017

100% Material Declaration Data Sheet for Virtex-5 FFG1136 RoHS 6/6

Average Weight : 10.3700 g

Component	Substance Description	CAS # or Description	% of component	Use in product	Component weight / substance weight (in grams)	Component % of total
Silicon die					0.521785	5.03%
	Silicon	7440-21-3	100.00	basis	0.521785	
Bump					0.018836	0.18%
	Tin	7440-31-5	98.20	basis	0.018497	
	Silver	7440-22-4	1.80	basis	0.000339	
Underfill					0.073000	0.70%
	Bisphenol F type liquid epoxy	9003-36-5	15.00	basis	0.010950	
	1,6-Bis(2,3-epoxypropoxy)naphthalene	27610-48-6	10.00	basis	0.007300	
	Bisphenol A type liquid epoxy	25068-38-6	5.00	basis	0.003650	
	Amine type hardener	trade secret	10.00	basis	0.007300	
	Silicon dioxide	60676-86-0	58.00	filler	0.042340	
	Carbon black	1333-86-4	1.00	color agent	0.000730	
Additives	trade secret	1.00	additives	0.000730		
Solder paste					0.008464	0.08%
	Tin	7440-31-5	96.50	metal	0.008168	
	Silver	7440-22-4	3.00	metal	0.000254	
	Copper	7440-50-8	0.50	metal	0.000042	
Capacitor 1					0.003600	0.03%
	Barium oxide, obtained by calcining witherite	1304-28-5	37.46	Ceramic	0.001349	
	Titanium dioxide	13463-67-7	18.73		0.000674	
	Misc	-	6.24		0.000225	
	Nickel	7440-02-0	17.95	Inner electrode	0.000646	
	Copper	7440-50-8	15.88	Out electrode	0.000572	
	Silicon dioxide	7631-86-9	1.41		0.000051	
	diboron trioxide; boric oxide	1303-86-2	0.35		0.000013	
	Nickel	7440-02-0	0.54	Plating1	0.000019	
Tin	7440-31-5	1.44	Plating2	0.000052		
Capacitor2					0.006880	0.07%
	Barium oxide, obtained by calcining witherite	1304-28-5	34.54	Ceramic	0.002376	
	Titanium dioxide	13463-67-7	17.27		0.001188	
	Misc	-	5.76		0.000396	
	Nickel	7440-02-0	31.9	Inner Electrode	0.002195	
	Copper	7440-50-8	8.52	Outer Electrode	0.000586	
	Silicon dioxide	7631-86-9	0.76		0.000052	
	diboron trioxide; boric oxide	1303-86-2	0.19		0.000013	
	Nickel	7440-02-0	0.29	Plating1	0.000020	
Tin	7440-31-5	0.77	Plating2	0.000053		
Heat sink					4.965400	47.88%
	Copper	7440-50-8	98.35	Main material	4.883471	
	Nickel	7440-02-0	1.65	Main material	0.081929	
Heat sink adhesive					0.209400	2.02%
	Aluminium Oxide Al2O3	-	80.00	Main material	0.167520	
	Dimethyl siloxane, dimethylvinyl-terminated	68083-19-2	20.00	Main material	0.041880	
Solder ball					0.951543	9.18%
	Tin	7440-31-5	95.50	Main material	0.908724	
	Silver	7440-22-4	4.00	Main material	0.038062	
	Copper	7440-50-8	0.50	Main material	0.004758	
Substrate					3.611092	34.82%
	Copper	7440-50-8	34.78		1.255937	
	Tin	7440-31-5	0.77		0.027805	
	Silver	7440-22-4	0.06		0.002167	
	Resin		0.10		0.003611	
	Core		44.65		1.612353	
	PP		4.39		0.158527	
	ABF		13.62		0.491831	
Solder Mask		1.63		0.058861		

Revision History

Date	Version	Description of Revisions
1/19/2017	1.0	Initial Xilinx release.

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.