



PK930(v1.0) October 25, 2017

# 100% Material Declaration Data Sheet for Ultrascale+ & Zynq Ultrascale+ FBVB900

Average Weight : 5.1033 g

Component	Substance Description	CAS # or Description	% of component	Use in product	Component weight / substance weight ( in grams)	Component % of total
Silicon die	Silicon	7440-21-3	100.00	basis	0.405437	7.945%
					0.405437	
Bump	Tin	7440-31-5	98.20	basis	0.017869	0.357%
	Silver	7440-22-4	1.80	basis	0.000328	
Underfill					0.056600	1.109%
	Bisphenol F type liquid	9003-36-5	15.00	basis	0.008490	
	1,6-Bis(2,3-	27610-48-6	10.00	basis	0.005660	
	Bisphenol A type liquid	25068-38-6	5.00	basis	0.002830	
	Amine type hardener	trade secret	10.00	basis	0.005660	
	Silicon dioxide	60676-86-0	58.00	filler	0.032828	
	Carbon black	1333-86-4	1.00	color agent	0.000566	
	Additives	trade secret	1.00	additives	0.000566	
Solder paste					0.008480	0.166%
	Tin	7440-31-5	85.40	metal	0.007242	
	Silver	7440-22-4	2.66	metal	0.000226	
	Copper	7440-50-8	0.44	metal	0.000037	
	Additives	trade secret	11.50	flux	0.000975	
Capacitor 1					0.001200	0.024%
	BaTiO3 type	1304-28-5	30.22	Ceramic	0.000363	
	Titanium dioxide	13463-67-7	15.11		0.000181	
	Misc	trade secret	5.04		0.000060	
	Nickel	7440-02-0	33.44	Inner electrode	0.000401	
	Copper	7440-50-8	11.87	Out electrode	0.000142	
	Silicon dioxide	7631-86-9	1.06		0.000013	
	diboron trioxide; boric	1303-86-2	0.26		0.000003	
	Nickel	7440-02-0	0.81	Plating1	0.000010	
	Tin	7440-31-5	2.19	Plating2	0.000026	
Capacitor 2					0.000920	0.018%
	BaTiO3 type	1304-28-5	31.67	Ceramic	0.000291	
	Titanium dioxide	13463-67-7	15.83		0.000146	
	Misc	trade secret	5.28		0.000049	
	Nickel	7440-02-0	26.67	Inner electrode	0.000245	
	Copper	7440-50-8	15.10	Out electrode	0.000139	
	Silicon dioxide	7631-86-9	1.34		0.000012	
	diboron trioxide; boric	1303-86-2	0.33		0.000003	
	Nickel	7440-02-0	1.00	Plating1	0.000009	
Tin	7440-31-5	2.78	Plating2	0.000026		
Solder ball					0.751829	14.732%
	Tin	7440-31-5	96.50	Main material	0.725515	
	Silver	7440-22-4	3.00	Main material	0.022555	
Substrate	Copper	7440-50-8	43.38		1.674744	75.650%
	Tin	7440-31-5	0.45		0.017373	
	Silver	7440-22-4	0.01		0.000386	
	Resin	N/A	0.12		0.004633	
	Core	N/A	38.78		1.497155	
	ABF	N/A	16.14		0.623107	
	Solder Mask	N/A	1.12		0.043239	

## Revision History

Date	Version	Description of Revisions
10/25/2017	1.0	Initial Xilinx Release.

## Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.